

Silica Flour Specification

Specification	Unit	Requirements	Result
SiO ₂	%	Min 85	90
Moisture	%	Max 3	2
L.O.I	%	Max 6	4
Residue on ASTM Sieve No: 200	%	Max 10	8
Accelerated Pozolonic Activity Index Portland Cement at 7 Days	%	Min 85	90

