

## BENTONITE OCMA Standard

Specification	Unit	Requirements
Yield	–	Min 16
Moisture	%	Max 13
Residue on ASTM sieve NO: 100 (Dry method )	Wt%	Max 2
Residue on ASTM sieve NO: 200 (Water method)	Wt%	Max 2.5

